


# G A L D A N A

---



120x120 R  
47¼"x47¼" R



60x120 R  
23¾"x47¼" R



100x100 R  
40"x40" R



25x50  
10"x20"

# Galdana

PORCELÁNICO ESMALTADO / GLAZED PORCELAIN TILE  
ACABADO PULIDO / POLISHED FINISH

LUX

47¼" x 47¼" R 120x120 R



Galdana White Pul 120x120 R



Galdana White Pul 120x120 R

P440R

# Galdana

PORCELÁNICO ESMALTADO / GLAZED PORCELAIN TILE  
ACABADO PULIDO / POLISHED FINISH

LUX

23<sup>3</sup>/<sub>4</sub>"x47<sup>1</sup>/<sub>4</sub>" R 60x120 R



Galdana White Pul 60x120 R



Galdana White Pul 60x120 R

P460R

# Galdana

PORCELÁNICO ESMALTADO / GLAZED PORCELAIN TILE  
ACABADO PULIDO / POLISHED FINISH

LUX

40"x40" R 100x100 R



Galdana White Pul 100x100 R



Galdana White Pul 100x100 R

P410R

# Galdana

REVESTIMIENTO PASTA ROJA / RED BODY WALL TILE  
ACABADO SATINADO / SATIN FINISH

10"x20" 25x50



Galdana White 25x50 / Star Galdana White 25x50



Galdana White 25x50 G1220



Star Galdana White 25x50 G1226

# Technical Characteristics

## Características técnicas

DESCRIPCIÓN DEL TEST TEST DESCRIPTION		NORMA STANDARD	GRUPO B1a Porcelánico esmaltado Glazed Porcelain Tile	GRUPO B1b Pasta porcelánica Porcelain Clay
Absorción de agua / Water absorption		UNE-EN ISO 10545-3	Ev ≤ 0,5%	0,5% < Ev ≤ 3%
Fuerza de rotura / Breaking Strength		UNE-EN ISO 10545-4	≥ 1300 N	≥ 1100 N
Resistencia a la flexión / Modulus of rupture		UNE-EN ISO 10545-4	≥ 35 N/mm <sup>2</sup>	≥ 30 N/mm <sup>2</sup>
Abrasion superficial / Surface Abrasion		UNE-EN-ISO 10545-7	A consultar según modelo Consult according to model	A consultar según modelo Consult according to model
Resistencia al cuarteo / Crazing resistance		UNE-EN ISO 10545-11	Requerido Requested	Requerido Requested
Resistencia a la helada / Frost resistance		UNE-EN ISO 10545-12	Requerido Requested	Requerido Requested
Resistencia química Chemical resistance	Productos domésticos y de piscina Household chemicals and swimming pool salts	UNE-EN ISO 10545-13	Mínimo clase B Minimum class B	Mínimo clase B Minimum class B
	Ácidos a baja concentración Low concentration of acids	UNE-EN ISO 10545-13	Mínimo clase LB Minimum class LB	Mínimo clase LB Minimum class LB
	Bases a baja concentración Low concentration of alkalis	UNE-EN ISO 10545-13	Mínimo clase LB Minimum class LB	Mínimo clase LB Minimum class LB
Resistencia a las manchas / Stain resistance		UNE-EN ISO 10545-14	Mínimo clase 3 Minimum Class 3	Mínimo clase 3 Minimum Class 3

## Symbology

### Simbología



## Packing List

PORCELANICO ESMALTADO / GLAZED PORCELAIN TILE									
Formato Nominal Nominal Size	Formato de trabajo Work size	Pzas/Cj	m <sup>2</sup> /Cj	Kg/Cj	Kg/m <sup>2</sup>	Pzs/Epl	Cjas/Epl	m <sup>2</sup> /Epl	Kg/Epl
120x120 R PUL	119x119 R	1	1,4161	34,50	24,36	36	36	50,98	1.300,00
60x120 R PUL	59x119 R	2	1,4042	33,06	23,54	72	36	50,55	1.215,00
100x100 R PUL	98x98 R	2	1,9208	46,48	24,20	40	20	38,42	950,00
REVESTIMIENTO PASTA ROJA / RED BODY WALL TILE									
25x50	25x50	13	1,6250	26,95	16,58	832	64	104,00	1.740,00
25x50 RELIEVE	25x50	12	1,5000	24,89	16,60	768	64	96,00	1.600,00

© Copyright KTL, S.L.U.

Reservados todos los derechos.

KTL se reserva el derecho de modificar las características de sus productos sin preaviso de ningún tipo.

Los acabados se dan a título indicativo, quedando bajo reserva los ajustes de los colores consecuencia de las técnicas de impresión. Por ello las fotografías de los productos expuestos no son contractuales.

All rights reserved.

KTL reserves the right to change the characteristics of its products without prior notice.

Information about the finishes of the goods is only provided as a guide. As a result of the printing techniques there might be differences between the colours printed in this catalogue and these of the real products. Colours shown in this catalogue are not contractual.

**KTLC**  
CERAMICA

Partida Casablanca nº 6 / 12593 Moncofar, Castellón. Spain

Phone: +34 964 584 069 / e-mail: info@ktlceramica.com / web: www.ktlceramica.com